

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C23C 22/05, 22/06, 22/53	A1	(11) International Publication Number: WO 95/21277 (43) International Publication Date: 10 August 1995 (10.08.95)
(21) International Application Number: PCT/US95/00977 (22) International Filing Date: 1 February 1995 (01.02.95) (30) Priority Data: 6/11695 3 February 1994 (03.02.94) JP (71) Applicant (for all designated States except US): HENKEL CORPORATION [US/US]; Suite 150, 140 Germantown Pike, Plymouth Meeting, PA 19462 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): AOYAMA, Masayuki [JP/JP]; 1681-5-401, Ogami, Hiratsuka-shi, Kanagawa-ken 254 (JP). OGINO, Takao [US/US]; 4245-2, Yokouchi, Hiratsuka-shi, Kanagawa-ken 254 (JP). (74) Agent: WISDOM, Norvell, E., Jr.; Henkel Corporation, 140 Germantown Pike, Suite 150, Plymouth Meeting, PA 19462 (US).		(81) Designated States: BR, CA, MX, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: SURFACE TREATMENT AGENT FOR ZINCIFEROUS-PLATED STEEL (57) Abstract A chromium-free aqueous liquid surface treatment agent that can impart both a good corrosion resistance and a good paint adherence to zinciferous-plated steel sheet contains as its essential components polyhydroxyaryl carboxylic acid and/or depside thereof and silane coupling agent with the formula $(YR)_mR_nSiX_{(4-m-n)}$, in which R denotes alkyl groups; X is the methoxy or ethoxy group; Y is the vinyl, amino, mercapto, glycidoxy, or methacryloxy group; m = 1 to 3; and n = 0 to (3-m). The total content of said essential components is preferably 1 to 50 weight %.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Description**SURFACE TREATMENT AGENT FOR ZINCIFEROUS-PLATED STEEL**Technical Field

The invention relates to an optimized surface treatment agent that imparts both an excellent corrosion resistance and an excellent paint adherence to the surface of steel, especially steel sheet, plated with zinc or zinc-containing alloy (hereinafter abbreviated as zinciferous-plated steel). The invention will be described below primarily with respect to use on steel sheet, but it is to be understood that any other shape of steel substrate may also be treated according to the invention.

Background Art

Zinciferous-plated steel sheet utilizes the principle of sacrificial zinc corrosion, which is a general method for preventing the corrosion of iron and steel. Zinciferous-plated steel sheet is used in a broad range of applications, extending over the automotive, building material, and household electrical appliance sectors. However, the corrosion product generated when zinc corrodes in the atmosphere produces so-called white rust on the steel sheet, which leads to a deterioration in appearance. Moreover, this white rust also impairs paint adherence to the plated steel sheet.

These problems are generally solved by subjecting the surface of zinciferous-plated steel sheet to a chromate treatment with a treatment bath whose main components are chromic acid, dichromic acid, or a salt thereof. This treatment produces a highly corrosion-resistant and strongly paint-adherent chromate film.

Unfortunately, the hexavalent chromium present in the chromate treatment baths used on zinciferous-plated steel sheet has a direct negative effect on the human body. This, and the recent increased demand for environmental protection, has created a desire to avoid the use of chromate treatments. In addition, the use of chromate treatments requires the implementation of special waste water treatment as stipulated in the Water Pollution Prevention Law, which drives up costs as a whole. Finally, when discarded or abandoned, chromate-treated zinciferous-plated steel sheet is classified as a chromium-containing waste and

therefore cannot be recycled.

One well-known non-chromate surface treatment method uses surface treatment agents based on tannic acid (tannic acid contains polyphenolic carboxylic acid). When zinciferous-plated steel sheet is treated with an aqueous solution of tannic acid, the zinc tannate produced by the reaction between tannic acid and zinc forms a protective coating. It is thought that the corrosion resistance of the zinciferous-plated steel sheet is improved through the action of this protective coating as a barrier to the infiltration of corrosive substances.

Japanese Patent Publication Number Sho 54-22781 [22,781/1979] teaches a tannic acid-based surface treatment method comprising the treatment of zinciferous-plated steel sheet with an aqueous solution that contains at least tannic acid and silica sol. This method forms an ultrathin surface film that has a rust-inhibiting activity. The problem with this method is that this film still cannot deliver a satisfactory corrosion resistance.

Otherwise, Japanese Patent Publication Number Sho 61-33910 [33,910/1986] teaches a method in which zinc-containing metal articles are first treated with a strongly alkaline ($\text{pH} \geq 12.5$) aqueous solution and are thereafter treated with an acidic aqueous solution whose main component is tannic acid. While the coating produced by this method has a relatively good corrosion resistance, this method requires a strongly alkaline treatment and a water rinse prior to the tannic acid treatment. This results in a poor productivity and poor economics.

Another surface treatment method is disclosed in Japanese Patent Publication Number Sho 58-15541 [15,541/1983]. In this method, the surface of zinciferous-plated steel sheet is treated with an aqueous solution containing organosilane coupling agent and one or both of water glass and sodium silicate. The surface film yielded by this method exhibits a good primary adherence, but a poor secondary adherence and a poor corrosion resistance.

Thus, no chromium-free surface treatment agent introduced to date is able to impart both an excellent corrosion resistance and an excellent paint adherence to zinciferous-plated steel sheet.

Disclosure of the InventionProblems to Be Solved by the Invention

The present invention takes as its object the introduction of a chromium-free surface treatment agent that solves the problems described above for the prior art by simultaneously providing the excellent corrosion resistance and excellent paint adherence required for zinciferous-plated steel sheet.

Summary of the Invention

A coating having both a high corrosion resistance and a strong paint adherence can be produced by treating the surface of zinciferous-plated steel sheet with a surface treatment agent that contains a particular type of silane coupling agent and at least one selection from polyhydroxyaryl carboxylic acids and dep-

sides of polyhydroxyaryl carboxylic acids. The invention was achieved based on this finding.

In specific terms, the surface treatment agent according to the invention for zinciferous-plated steel sheet characteristically comprises, preferably consists essentially of, or more preferably consists of, water and the following essential components:

- (A) a component selected from the group consisting of polyhydroxyaryl carboxylic acids and depsides of polyhydroxyaryl carboxylic acids; and
- (B) a component selected from the group consisting of silane coupling agents with the following general formula (I):



in which R denotes an alkyl group, which may be the same or different from one of the m YR and the n R moieties to another; X denotes a methoxy or ethoxy moiety; Y denotes a moiety selected from the group consisting of vinyl, amino, mercapto, glycidoxo, and methacryloxy moieties, which may be the same or different from one of the m YR moieties to another; m is an integer with a value from 1 to 3; and n is an integer with a value of 0 to (3-m); and optionally, one or more of:

- (C) water miscible monoalcohols;
- (D) metal cations with a valence of two or more; and
- (E) accelerator anions.

It is preferred, furthermore, that the total content of essential components (A) and (B) in the surface treatment agent according to the invention should be 1 to 50 weight %.

Detailed Description of the Invention

5 Zinciferous-plated steel which can be treated with the surface treatment agent of the invention encompasses steel coated with zinc or a zinc alloy, for example, Zn/Fe alloy, Zn/Ni alloy, Zn/Al alloy, and the like.

 Polyhydroxyaryl carboxylic acids usable by the present invention must have at least two hydroxyl substituents and at least one carboxyl substituent on
10 a single aromatic nucleus. Such acids are exemplified by gallic acid, protocatechuic acid, galloxyaric acid, and the like. Suitable as the depsides of polyhydroxyaryl carboxylic acids are, for example, meta-digallic acid, trigallic acid, diplo-schistesic acid, tannin, tannic acid, and so forth. The tannin used in the present invention is a general term for substances extractable by hot water from the
15 seeds, fruits, shells, leaves, roots, wood, and bark of plants and able to convert raw animal hides into leather. Tannic acid is the tannin obtained from Chinese or Turkish nutgall, etc. The type and quantity of addition of these substances is not critical.

 Any silane coupling agent that has a chemical structure with general formula (I) may be used in the present invention. For example, compounds from the
20 following groups (a) - (c) can be used and are generally preferred.

(a) glycidoxy-functional silane coupling agents

 e.g., 3-glycidoxypropyl trimethoxy silane
 3-glycidoxypropyl methyl dimethoxy silane
25 2-(3,4-epoxycyclohexyl)ethyl trimethoxy silane

(b) amino-functional silane coupling agents

 e.g., N-(2-aminoethyl)-3-aminopropyl methyl dimethoxy silane
 N-(2-aminoethyl)-3-aminopropyl trimethoxy silane
 3-aminopropyl triethoxy silane

30 (c) mercapto-functional silane coupling agents

 e.g., 3-mercaptopropyl trimethoxy silane.

No specific restrictions apply to the content of these silane coupling agents in the surface treatment agent.

The surface treatment agent of the invention may in general be prepared by dissolving or dispersing the aforementioned essential components in water.

5 While the total concentration of the essential components is not specifically restricted, the sum of the concentrations of the essential components, i.e., silane coupling agent + polyhydroxyaryl carboxylic acid(s) and/or depside(s) of polyhydroxyaryl carboxylic acid(s) is preferably 1 to 50 weight %. When the total amount of these essential components falls below 1 weight %, the treated zinciferous-plated steel sheet will not always exhibit the good corrosion resistance that is the goal of the present invention. On the other hand, a total amount of essential components in excess of 50 weight % is uneconomical because no further improvement in corrosion resistance is obtained for the treated zinciferous-plated steel sheet at such values. The weight ratio between subject essential components is preferably {polyhydroxyaryl carboxylic acid(s) and/or depside(s) thereof}:
10 {silane coupling agent} = 10 : 1 to 1 : 2, or preferably 10 : 1 to 1 : 1.

The surface treatment agent according to the invention may contain additives in addition to the essential components already discussed above. Metal ions may be added in order to improve the insolubility of the treated zinciferous-plated steel sheet. Metal ions usable for this purpose are exemplified by iron,
20 nickel, manganese, cobalt, zinc, aluminum, calcium, and magnesium ions, with zinc and magnesium ions being particularly preferred. In addition, a reaction accelerator may be added in order to accelerate the reaction with the surface of the zinciferous-plated steel sheet. Preferred for use as this reaction accelerator are,
25 for example, phosphate ions, nitrate ions, fluoride ions, and organic acids other than those that are part of component (A). Fluoride ions are particularly preferred as the reaction accelerator. Finally, no particular restrictions apply to the sources of the ions and quantities of addition for the described additives.

An additive that is generally preferred is optional component (C) as described above, of which methanol is the most preferred embodiment. Independently, a concentration of optional component (C) in the range from 1 to 30, more
30

preferably 5 to 15, or still more preferably 9 to 11, weight % is preferred in the treatment compositions according to the invention.

No particular restriction obtains on the method for treating zinciferous-plated steel sheet using the surface treatment agent of the invention, and, for example, immersion, spray, and roll coating methods are applicable. Nor is the treatment temperature or treatment time crucial, but in general the treatment temperature is preferably 10° C to 40° C and the treatment time is preferably 0.1 to 10 seconds.

Zinciferous-plated steel sheet treated with the surface treatment agent of the invention exhibits both an excellent corrosion resistance and an excellent paint adherence. In regard to the improved corrosion resistance, the polyhydroxyaryl carboxylic acid or deposite thereof in the treatment agent is believed to react with the zinc to form a protective coating on the surface of the zinciferous-plated steel sheet. This protective coating then would prevent the infiltration of corrosive substances, thus yielding the improved corrosion resistance. The improved paint adherence is believed to occur as the result of adsorption of the functional groups in the silane coupling agent to the surface of the zinciferous-plated steel sheet.

The invention is explained in greater detail below through working examples, which, however, should not be construed as placing particular limits on the scope of the invention.

Examples

The following materials and procedure for cleaning the steel sheet were used in the examples.

1. Test materials

The following were used as the zinciferous-plated steel sheet substrates: commercial steel sheet (sheet thickness = 0.6 mm) hot-dip galvanized on both sides (denoted below as "HDG" material, coating weight = 40 g/m²) or electrogalvanized on both sides (denoted below as "EG" material, coating weight = 20 g/m²).

2. Cleaning procedure

A moderately alkaline degreaser (FINECLEANER™ 4336, commercially available from Nihon Parkerizing Company, Limited, Tokyo) was used a concentration of 20 g/L. The dirt and oil adhering on the surface were removed by spraying the zinciferous-plated steel sheet with the aqueous degreaser solution using a treatment temperature of 60° C and a treatment time of 20 seconds. The alkali remaining on the surface of the treated steel sheet was then washed off using tap water to yield the clean zinciferous-plated steel sheet surface.

Example 1

The EG material, cleaned as described above, was immersed at room temperature for 20 seconds in a surface treatment bath prepared by dissolving 0.5 weight % of gallic acid, 0.5 weight % of 3-glycidoxypopyl trimethoxy silane, and 10 weight % of methanol in deionized water. This was followed by draining and drying to a sheet temperature of 100° C.

Example 2

The treatment procedure of Example 1 was executed on the HDG material instead of the EG material used in Example 1.

Example 3

The surface of the EG material, cleaned as described above, was roll coated with a surface treatment bath prepared by dissolving 5.0 weight % of Chinese nutgall tannin, 3.4 weight % of 3-glycidoxypopyl methyl dimethoxy silane, and 10 weight % methanol in deionized water. This was followed by drying to a sheet temperature of 100° C.

Example 4

The treatment procedure of Example 3 was executed on the HDG material instead of the EG material used in Example 3.

Example 5

The surface of the EG material, cleaned as described above, was roll coated with a surface treatment bath prepared by dissolving 10 weight % of protocatechuic acid, 2.5 weight % of 3-aminopropyl triethoxy silane, and 10 weight % of methanol in deionized water. This was followed by drying to a sheet temperature of 100° C.

Example 6

The treatment procedure of Example 5 was executed on the HDG material instead of the EG material used in Example 5.

Example 7

5 The EG material, cleaned as described above, was immersed at room temperature for 20 seconds in a surface treatment bath prepared by dissolving 18.0 weight % of quebracho tannin, 32.0 weight % of 3-mercaptopropyl trimethoxy silane, and 10 weight % of methanol in deionized water. This was followed by draining with a wringer roll and drying to a sheet temperature of 100° C.

10 Example 8

The treatment procedure of Example 7 was executed on the HDG material instead of the EG material used in Example 7.

Comparative Example 1

15 The EG material, cleaned as described above, was immersed at room temperature for 20 seconds in a comparative treatment bath prepared by dissolving 5.0 weight % of Chinese nutgall tannin in deionized water. This was followed by draining using a wringer roll and drying to a sheet temperature of 100° C.

Comparative Example 2

20 The treatment procedure of Comparative Example 1 was executed on the HDG material instead of the EG material used in Comparative Example 1.

Comparative Example 3

25 The EG material, cleaned as described above, was sprayed for 10 seconds at room temperature with a comparative treatment bath prepared by dissolving 5.0 weight % of 3-glycidoxypentyltrimethoxysilane, 10 weight % of methanol, and 25 weight % of 20 % silicic acid sol in deionized water. This was followed by draining using a wringer roll and drying to a sheet temperature of 100° C.

Comparative Example 4

30 The treatment procedure of Comparative Example 3 was executed on the HDG material instead of the EG material used in Comparative Example 3.

Evaluation Testing

The products from Examples 1 to 8 and Comparative Examples 1 to 4 were tested by the following methods.

(1) Corrosion resistance

5 The resistance to white rusting was tested by the salt spray test of JIS Z-2371. The following scale was employed to report the results.

	+	+	+	:	no abnormalities
	+	+	:	area of white rust development less than 5 %	
	+	:	area of white rust development is 5 to 10 %		
10	x	:	area of white rust development is 11 to 50 %		
	x	x	:	area of white rust development is 51 % or greater	

(2) Paint adherence

15 After treatment with a surface treatment agent as described above, the zinciferous-plated steel sheet was coated with paint (Delicon #700 from Dainippon Toryo Kabushiki Kaisha) and baked at 140° C for 20 minutes to yield a 25 micrometer-thick paint film.

(i) Primary paint adherence

20 Crosscut test: a crosshatch pattern of 1 mm x 1 mm squares was cut in the paint film on the product's surface using an NT cutter, and the number of squares remaining after peeling with adhesive tape was counted.

Crosscut/Erichsen test: the specimen was extruded 5 mm after the crosscut evaluation, and the number of squares remaining after peeling with adhesive tape was counted.

(ii) Secondary paint adherence

25 The painted sheet was immersed in boiling pure water for 2 hours and was then evaluated by the crosscut test and crosscut/Erichsen test as described above for primary paint adherence.

30 The results of these tests are shown in Table 1 below. The results in Table 1 confirm that excellent values for both corrosion resistance and paint adherence (both primary and secondary) were obtained for Examples 1 to 8 of the invention. In Comparative Examples 1 to 4, on the other hand, no treatment gave good results in all the tests conducted, and the results from the secondary paint

Table 1: RESULTS OF THE EVALUATION TESTS

Example ("E") or Comparison Ex- ample ("CE") Number	Corrosion Resistance, 24 Hr. Salt Spray	Primary Paint Adherence		Secondary Paint Adherence	
		Crosscut Only	Crosscut/ Erichsen	Crosscut Only	Crosscut/ Erichsen
E 1	++	100/100	100/100	100/100	100/100
E 2	++	100/100	100/100	100/100	100/100
E 3	+++	100/100	100/100	100/100	100/100
E 4	+++	100/100	100/100	100/100	100/100
E 5	+++	100/100	100/100	100/100	99/100
E 6	+++	100/100	100/100	100/100	98/100
E 7	+++	100/100	100/100	100/100	97/100
E 8	+++	100/100	100/100	100/100	96/100
CE 1	+	100/100	100/100	88/100	47/100
CE 2	+	100/100	100/100	82/100	51/100
CE 3	xx	100/100	100/100	88/100	29/100
CE 4	xx	100/100	100/100	80/100	33/100

Notes for Table 1

The results reported for the crosscut and crosscut/Erichsen tests are the number of squares remaining unpeeled after tape peeling before the virgule ("/") out of the number of total squares after the virgule.

adherence tests were particularly inferior to the results given by the invention examples.

Benefits of the Invention

Zinciferous-plated steel treated with the surface treatment agent according to the invention exhibits an excellent performance in both critical areas of corrosion resistance and paint adherence. The surface treatment agent of the invention is also very safe and highly advantageous in terms of environmental protec-

tion and recyclability. In particular, since it is clear that future restrictions on sol-
vents will necessitate a change from solvent-based cleaning to water-based
cleaning, the treatment agent of the invention will be particularly effective in those
sectors in which environmental problems might occur due to chromium elution
5 from the surface of chromated zinciferous-plated steel sheet.

Claims

1. An aqueous liquid surface treatment composition for zinciferous-plated steel, said composition comprising water and:

- (A) a component selected from the group consisting of polyhydroxyaryl carboxylic acids and depsides of polyhydroxyaryl carboxylic acids; and
 (B) a component selected from the group consisting of silanes conforming to the general formula (I):



in which R denotes an alkyl group, which may be the same or different from one of the m YR and the n R moieties to another; X denotes a methoxy or ethoxy moiety; Y denotes a moiety selected from the group consisting of vinyl, amino, mercapto, glycidoxo, and methacryloxy moieties, which may be the same or different from one of the m YR moieties to another; m is an integer with a value from 1 to 3; and n is an integer with a value of 0 to (3-m).

2. A composition according to claim 1, wherein components (A) and (B) jointly constitute from 1 to 50 weight % of the composition.

3. A composition according to claim 2, wherein Y is selected from the group consisting of glycidoxo, amino, and mercapto.

4. A composition according to claim 3, additionally comprising:

- (C) from 9 to 11 weight % of methanol; and, optionally, one or more of the following:
 (D) metal cations with a valence of two or more; and
 (E) accelerator anions.

5. A composition according to claim 2, additionally comprising:

- (C) from 5 to 15 weight % of a component selected from water miscible monoolcohols; and, optionally, one or more of the following:
 (D) metal cations with a valence of two or more; and
 (E) accelerator anions.

6. A composition according to claim 1, additionally comprising:
- (C) from 1 to 30 weight % of a component selected from water miscible mon-
oalcohols; and, optionally, one or more of the following:
 - (D) metal cations with a valence of two or more; and
 - 5 (E) accelerator anions.
7. A composition according to claim 1, wherein Y is selected from the group
consisting of glycidoxo, amino, and mercapto.
8. A composition according to claim 7, additionally comprising:
- 10 (C) from 1 to 30 weight % of a component selected from water miscible mon-
oalcohols; and, optionally, one or more of the following:
 - (D) metal cations with a valence of two or more; and
 - (E) accelerator anions.
9. A process for treating a steel substrate by contacting the substrate with
a composition according to any one of claims 1 - 8.
- 15 10. A process according to claim 9, wherein the temperature of the
composition during contact is from 10 to 40 ° C and the time of contact is from
0.1 to 10 seconds.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/00977

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C23C 22/05, 22/06, 22/53

US CL : 148/243, 259, 274

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 148/243, 259, 274

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A, E	US, A, 5,389,405 (PURNELL et al) 14 FEBRUARY 1995.	1-10
A, E	US, A, 5,393,605 (MIYOSHI et al) 28 FEBRUARY 1995.	1-10
A	JP, A, 55-021509 (TOA GOSEI CHEM IND LTD) 15 FEBRUARY 1980.	1-10
A	JP, A, 59-116381 (MITSUI MINING & SMELTING) 05 JULY 1984.	1-10

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	* T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A document defining the general state of the art which is not considered to be of particular relevance	* X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
* E earlier document published on or after the international filing date	* Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
* L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* & document member of the same patent family
* O document referring to an oral disclosure, use, exhibition or other means	
* P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

29 MARCH 1995

Date of mailing of the international search report

24 APR 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

ANTHONY GREEN

Telephone No. (703) 308-0661